



Wallbarn - Technical Datasheet

Geotextile PECT 300 GSM



1m x 50m Roll: GE-PE-PECT-0300-MINI-Z

2m x 50m Roll: GE-PE-PECT-0300-Z

Widths of 3, 4, 5 & 6 metres available on special order.

Product Description

Nonwoven geotextile made with polyester, needle punched and calandered. Produced **without using of any glues or chemical binders** and postconsumer raw material. Ideal as a separation, filtration or protection membrane on domestic projects.

Made from recycled, multi-coloured, polyester fibre. Specific weight of polymer is 0.38 kg/dm³.

Wallbarn Ltd
Unit 16 Capital Business Centre
22 Carlton Road, South Croydon. CR2 0BS

IMS.T.1036.v1

Phone : 0208 916 2222 Email : sales@wallbarn.com Website : www.wallbarn.com



Wallbarn - Technical Datasheet

Physical Properties	Standard	Value	Units	Tolerance %	Tolerance Units
Mass per unit area	EN ISO 9864	300	g/m ²	+/- 10	+/- 30
Thickness at: 2 kPa	EN ISO 9863-1	1.20	mm	+/- 20	+/- 0.24

Mechanical Properties	Standard	Value	Units	Tolerance	Tolerance Units
Tensile Strength	EN ISO 10319 MD	2.4	kN/m	-15	-0.4
	EN ISO 10319 CMD	2.5	kN/m	-15	-0.4
Elongation at maximum load	EN ISO 10319 MD	50	%	+/- 30	+/- 15
	EN ISO 10319 CMD	60	%	+/- 30	+/- 18
Static puncture resistance (CBR)	EN ISO 12236	0.50	kN	-30	-0.15
Dynamic puncture resistance	EN ISO 13433	36	mm	+30	+11
Pyramidal puncture resistance	EN 14574	200	N	-20	-40

µm = Micrometre

mm/s = Millimetre per second

kJ/m² = Kilojoule per square metre

MD = Machine Direction/Longitudinal

kg/dm³ = Kilogram per cubic decimetre

kN = Kilonewton

mm = Millimetre

g/m² = Gram per square metre

kN/m = Kilonewton per metre

m³/ms = Cubic metre per millisecond

CMD = Cross Machine Direction/Trasversal

Wallbarn Ltd

IMS.T.1036.v1

Unit 16 Capital Business Centre

22 Carlton Road, South Croydon. CR2 0BS

Phone : 0208 916 2222 Email : sales@wallbarn.com Website : www.wallbarn.com



Wallbarn - Technical Datasheet

Hydraulic Properties	Standard	Value	Units	Tolerance	Tolerance Units
Velocity index	EN ISO 11058	60	mm/s	-30	-18
Characteristic opening size	EN ISO 12956	55	µm	+/- 30	+/- 17

Durability Properties	Standard	
Weathering resistance	EN 12224	To be covered within 15 days from the day of installation.
Service Life		Forecast minimum durability of 5 years in natural ground with 4<pH<9 and soil temperature < 25°C.

µm = Micrometre

mm/s = Millimetre per second

kJ/m² = Kilojoule per square metre

MD = Machine Direction/Longitudinal

kg/dm³ = Kilogram per cubic decimetre

kN = Kilonewton

mm = Millimetre

g/m² = Gram per square metre

kN/m = Kilonewton per metre

m³/ms = Cubic metre per millisecond

CMD = Cross Machine Direction/Trasversal

The values given are an average obtained in our laboratories and in official testing institutes.

The confidence level is 95%.

We reserve the right to make changes at any time without notice.

The material is produced according the quality management system of EN ISO 9001:2008.

Please refer to [GRO code](#) and other relevant building regulations before specifying.

Wallbarn Ltd

IMS.T.1036.v1


Unit 16 Capital Business Centre
22 Carlton Road, South Croydon. CR2 0BS

Phone : 0208 916 2222 Email : sales@wallbarn.com Website : www.wallbarn.com




Wallbarn - Technical Datasheet

MAIN FUNCTIONS




SEPARATION

Separation & retaining of soil and/or filling materials to stabilise groundworks



FILTRATION

Retaining soil or other particles while allowing the passage of moisture



PROTECTION

Preventing compression or puncture damage to delicate membranes beneath



Wallbarn Ltd

Unit 16 Capital Business Centre
22 Carlton Road, South Croydon. CR2 0BS

IMS.T.1036.v1

Phone : 0208 916 2222 Email : sales@wallbarn.com Website : www.wallbarn.com